

# SuperGlaze® MIG HD 5356

## TOP FEATURES

- Designed for heavy duty applications
- Reduced shavings and improved feedability
- General purpose filler alloy for welding 5XXX series alloys

## TYPICAL APPLICATIONS

- Shipbuilding
- Railway Industry
- Automotive
- Storage tanks
- Power Industry

## CLASSIFICATION

|                |                        |
|----------------|------------------------|
| AWS A5.10      | ER5356                 |
| EN ISO 18273-A | S Al 5356 (AlMg5Cr(A)) |

## SHIELDING GASES (ACC. EN ISO 14175)

|           |                             |
|-----------|-----------------------------|
| I1        | Inert gas Ar (100%)         |
| I3        | Inert gas Ar+ 0.5-95% He    |
| Flow rate | 14.2-23.6 l/min (for Argon) |

## APPROVALS

| ABS | LR | BV | RINA | TÜV | DB | CE |
|-----|----|----|------|-----|----|----|
| +   | +  | +  | +    | +   | +  | +  |

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

| Al   | Si   | Fe   | Cu   | Mn   | Mg   | Cr   | Zn    | Ti   | Be     |
|------|------|------|------|------|------|------|-------|------|--------|
| bal. | 0.05 | 0.09 | 0.03 | 0.12 | 4.90 | 0.08 | <0.01 | 0.15 | 0.0002 |

Notes: Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

|                | Shielding gas | Condition* | Yield strength (MPa) | Tensile strength (MPa) | Elongation (%) |
|----------------|---------------|------------|----------------------|------------------------|----------------|
| Typical values | I1            | AW         | 110-120              | 240-296                | 17-26          |

\* AW = As welded

## PACKAGING AND AVAILABLE SIZES

| Wire diameter (mm) | Packaging | Weight (kg) | Item number |
|--------------------|-----------|-------------|-------------|
| 1,2                | SPOOL     | 7.0         | ED703770    |
| 1,6                | SPOOL     | 7.0         | ED703804    |

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.  
Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.