

# ELT 600S

## TOP FEATURES

- Designed for nickel base electroslag cladding
- Excellent welding characteristics
- High hot cracking resistance
- Perfectly suitable for the standard and high cladding welding speeds

## CLASSIFICATION

Flux	EN ISO 14174: ES A FB 2B
------	--------------------------

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

Wire grade	C	Mn	Si	Cr	Ni	Mo	Nb	Fe
CladStrip 625	0.02	0.2	0.4	20.6	bal.	8.6	3.2	4.3

## FLUX CHARACTERISTICS

Current type	DC+
Basicity (Boniszewski)	4
Redrying	300-350°Cx2h
Grain size (EN-ISO 14174)	2-20

## PACKAGING AND AVAILABLE SIZES

Packaging	Weight (kg)	Item number
DRY BAG	25.0	W000384602

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.  
Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.