

CARBOFIL 1 GOLD

TOP FEATURES

- Exceptional arc stability, minimal spatters and smooth bead profile
- Low presence of silicates
- Available in all packagings from spools to drums

TYPICAL APPLICATIONS

- General fabrication
- Heavy Fabrication
- Automotive
- Structural fabrication
- Robotics

CLASSIFICATION

AWS A5.18	ER70S-6
EN ISO 14341-A	G 42 3 C1 3Si1
	G 42 4 M21 3Si1

SHIELDING GASES (ACC. EN ISO 14175)

C1	Active gas 100% CO ₂
M14	Mixed gas Ar+ 0.5-5% CO ₂ + >0,5-3% O ₂
M21	Mixed gas Ar+ >15-25% CO ₂

APPROVALS

ABS	LR	DNV	TÜV	DB	CE
+	+	+	+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	P	S
0.08	1.4	0.9	≤0.025	≤0.025

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)		
						+20 °C	-20 °C	-40 °C
Typical values	M21	AW	≥420	500-640	≥24	≥90	≥70	≥47
	C1	AW	≥420	500-640	≥22	≥70	≥47	

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
0.8	SPOOL (B300)	16.0	G08K016P6E11
	DRUM	300.0	G08D300E6E11
1.0	SPOOL (S300)	15.0	G10P015P6E11
	SPOOL (B300)	16.0	G10K016P6E11
	SPOOL (BS300)	16.0	G10L016P6E11, G10L016PSE11
	DRUM	300.0	G10D300E6E11
1.2	SPOOL (B300)	16.0	G12K016P6E11
	SPOOL (BS300)	16.0	G12L016P6E11
	DRUM	300.0	G12D300E6E11
	DRUM	600.0	G12D600E6Z11
1.32	SPOOL (BS300)	16.0	G13L016PSE11
1.6	SPOOL (B300)	16.0	G16K016P6E11

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.