ULTRAFIL 1

TOP FEATURES

- Good performances in terms of feedability and weldability
- Stable arc and low spatter
- High productivity

TYPICAL APPLICATIONS

- General fabrication
- Heavy Fabrication
- Automotive

CLASSIFICATION

AWS A5.18 ER70S-6 EN ISO 14341-A G 42 3 C1 3Si1

G 42 4 M21 3Si1

SHIELDING GASES (ACC. EN ISO 14175)

C1 Active gas 100% CO₂

M14 Mixed gas Ar+ 0.5-5% CO₂+ 0,5-3% O₂

M21 Mixed gas Ar+ >15-25% CO₂

APPROVALS

ΤÜV	DB	CE
+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

С	Mn	Si	Р	S
0.08	1.4	0.9	≤0.025	≤0.025

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Chielding gas	Condition*	Yield strength	Tensile strength	Elongation	Impact ISO-V (J)		
	Shielding gas	Condition	(MPa)	(MPa) (%)		+20°C	-30°C	-40°C
Typical values	M21	AW	≥420	500-640	≥24	≥90	≥70	≥47
	C1	AW	≥420	500-640	≥22	≥70	≥47	

^{*} AW = As welded

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
0.8	SPOOL (B300)	16.0	E08K016P6E11
	SPOOL (BS300)	16.0	E08L016P6E11
1.0	SPOOL (B300)	16.0	E10K016P6E11
	SPOOL (BS300)	16.0	E10L016P6E11
1.2	SPOOL (B300)	16.0	E12K016P6E11
	SPOOL (BS300)	16.0	E12L016P6E11



TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.

