

LNM MoNiVa

TOP FEATURES

- Excellent mechanical properties.
- For low temperature applications down to -40°C.
- Low heat inputs are recommended to obtain optimum joint mechanical properties.

TYPICAL APPLICATIONS

- Infrastructures
- Earthmoving
- Cranes
- Structural Steels

CLASSIFICATION

AWS A5.28 ER110S-G
EN ISO 16834-A G 69 4 M21 Mn3Ni1CrMo

SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ >15-25% CO2

APPROVALS

TÜV	DB	CE
+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL WIRE

C	Mn	Si	Ni	Cr	Mo	V	Cu
0.08	1.7	0.44	1.35	0.23	0.3	0.08	0.25

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -40°C
Typical values	M21	AW	710	790	20	70

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
0.8	SPOOL (B5300)	15.0	581218
1.0	SPOOL (B300)	16.0	S10K016PME01
	DRUM	250.0	S10D250EMS01
1.2	SPOOL (S300)	15.0	S12P015PMC01
	SPOOL (B300)	16.0	S12K016PME01
	DRUM	250.0	S12D250EMS01
1.4 MM	DRUM	250.0	S14D250EMS01

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.