

SAFDUAL 206A

The general purpose **metal cored wire** for M21 shielding gas.



SAF-FRO

www.saf-fro.com

SAFDUAL
EASY TO USE AND EXCELLENT OPERABILITY

SAFDUAL 206A

AWS 5.18: E70C-6M H4

EN ISO 17632-A: T 42 2 M M 1 H5



Advantages:

- High quality metal cored wire for welding with M21 gas
- Excellent arc stability and high deposition rate
- Regular welds with reduced amount of silicates
- Superior product consistency with optimal alloy control
- Suitable for single and multi-pass automatic welding
- Diffusible hydrogen below 4 ml/100g

Welding positions (ISO/ASME)



PA/1G



PB/2F



PC/2G



PE/4G



PF/3Gu

Chemical composition, weld metal, M21 (wt. %):

C	Mn	Si	P	S
0,05	1,35	0,6	≤0,015	≤0,023

Mechanical properties, weld metal, AW, M21 gas:

Re (MPa)	Rm (MPa)	A (%)	CVN @-20°C (J)
>420	500-640	26	>90

Packaging data

Packaging Type diam (mm)	B300 16 kg	Drum 200 kg
1,0	W000281619	
1,2	W000281622	W000281624