

# Outershield® 500CT-H

## TOP FEATURES

- For welding in all positions, except vertical down
- Superior weldability, low spatter, good bead appearance
- Outstanding operator appeal

## TYPICAL APPLICATIONS

- Welding of weather resistant steels
- Steel construction

## CLASSIFICATION

|                |                   |
|----------------|-------------------|
| AWS A5.29      | E81T1-GM          |
| EN ISO 18276-A | T 50 5 Z P M 2 H5 |

## CURRENT TYPE

DC+

## WELDING POSITIONS

All except vertical down

## SHIELDING GASES (ACC. EN ISO 14175)

|           |   |
|-----------|---|
| M21       | Mixed gas Ar+ (>15-25%) CO <sub>2</sub> |
| Flow rate | 15-25 l/min                             |

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

| Shielding gas | C    | Mn  | Si  | P     | S     | Ni   | Cu   | HDM        |
|---------------|------|-----|-----|-------|-------|------|------|------------|
| M21           | 0.04 | 1.3 | 0.2 | 0.014 | 0.010 | 0.84 | 0.39 | 4 ml/100 g |

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

|                | Shielding gas | Condition* | Yield strength (MPa) | Tensile strength (MPa) | Elongation (%) | Impact ISO-V (J) -50°C |
|----------------|---------------|------------|----------------------|------------------------|----------------|------------------------|
| Required:      |               |            | min. 470             | 550-690                | min. 19        |                        |
| EN ISO 18276-A |               |            | min. 500             | 560-720                | min. 18        | min. 47                |
| Typical values | M21           | AW         | 580                  | 610                    | 23             | 80                     |

\* AW = As welded

## PACKAGING AND AVAILABLE SIZES

| Wire diameter (mm) | Packaging    | Weight (kg) | Item number |
|--------------------|--------------|-------------|-------------|
| 1.2                | SPOOL (B300) | 16.0        | 942781N     |

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.