

Outershield® 690-H

TOP FEATURES

- All position gas shielded rutile flux cored wire, for high strength steel grades like grade S690
- Outstanding operator appeal
- Excellent mechanical properties (CVN >50J) at -40°C

TYPICAL APPLICATIONS

- Steel construction
- Offshore
- Pipeline

CLASSIFICATION

AWS A5.29 E111T1-K3M-JH4
EN ISO 18276-A T 69 4 Z P M 2 H5

CURRENT TYPE

DC+

WELDING POSITIONS

All except vertical down

SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ (>15-25%) CO₂
Flow rate 15-25 l/min

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

Shielding gas	C	Mn	Si	P	S	Ni	Mo	HDM
M21	0.06	1.5	0.2	0.015	0.010	2.0	0.3	3 ml/100 g

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)		
						-30°C	-40°C	-46°C
Required: AWS A5.29			min. 680	760-900	min. 15	min. 27		
EN ISO 18276-A			min. 690	770-940	min. 17		min. 47	
Typical values	M21	AW	780	810	18	85	80	65

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.2	SPOOL (S200)	4.5	942415
	SPOOL (B300)	16.0	942422N
	SPOOL (S300)	16.0	942453EN
1.6	SPOOL (S300)	16.0	942447N

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.