

FLUXOFIL 18HD

TOP FEATURES

- Seamless copper coated special rutile cored wire for welding of weathering steels such as Patinax or Cor-ten.
- Excellent weldability. Very good slag removal, regular bead profile and side wall wetting.
- Flux fill ration and current capacity designed to deliver optimal all positional performance.
- Designed for mix gas
- Easy slag removal, regular bead profile and side wall wetting

CLASSIFICATION

AWS A5.29 E81T1-GM-H4
EN ISO 17632-A T 50 3 Z P M21 1 H5

CURRENT TYPE

DC+

WELDING POSITIONS

All positions

SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ >15-25% CO₂

APPROVALS

RINA

+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	Cr	Ni	Cu
0.04	1.1	0.5	0.6	0.6	0.7

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -30°C
Typical values	M21	AW	≥500	560-690	≥21	≥47

* AW = As welded

Gas test: 82% Ar + 18% CO₂

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.2	SPOOL (B300)	16.0	W000281189

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.