# **SAFDUAL 128**

#### **TOP FEATURES**

- Rutile 0.9%Ni flux cored wire with excellent all-positional weldability and good impact toughness at -50°C.
- Can be welded in all positions with one setting of parameters.
   Ideal for offshore and naval shipyard applications. To be used with Ar/CO₂ gas shielding.
- Best in class welding performance and productivity in positional welding.
- Optimal solution for welding of wind mill foundations, offshore and steel constructions.
- Can be applied for applications requiring CTOD testing.
- Meets NACE MR-0175 requirements

#### **TYPICAL APPLICATIONS**

- Offshore
- Wind tower foundations
- Steel construction

#### CLASSIFICATION

AWS A5.29 E81T1-Ni1M-H4
EN ISO 17632-A T 46 5 1Ni P M 1 H5
EN ISO 17632-B T 55 5 T1-1MA-N1-UH5

#### **CURRENT TYPE**

DC+

#### **WELDING POSITIONS**

All positions

#### **SHIELDING GASES (ACC. EN ISO 14175)**

M21 Mixed gas Ar+ >15-25% CO<sub>2</sub>

#### **APPROVALS**

•	AI I NOVALO						
	ABS	LR	DNV				
	+	+	+				

# CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

С	Mn	Si	Р	S	Ni
0.05	1.3	0.4	≤0.015	≤0.015	0.85

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Chielding gas	Condition*	Yield strength	Tensile strength	Elongation (%)	Impact ISO-V (J)	
	Shielding gas	Condition	(MPa)	(MPa)		-40°C	-50°C
Typical values	M21	AW	≥460	550-690	≥22	≥80	≥60

<sup>\*</sup> AW = As welded

Gas test: 82% Ar+18% CO₂

### **PACKAGING AND AVAILABLE SIZES**

Wire diameter (mm)	Packaging	Weight (kg)	Item number	
1.2	SPOOL (B300)	16.0	W000281695	



#### **TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to <a href="www.lincolnelectric.eu">www.lincolnelectric.eu</a> for any updated information.

