

LNT 304L

TOP FEATURES

- The low carbon content reduces the propensity to intergranular carbide precipitation, which increases the resistance to intergranular corrosion without the use of stabilizers.
- The weld metal provides good corrosion resistance properties to intergranular attack from a range of liquid media at service temperatures up to 300 °C.
- Excellent mechanical strength and corrosion resistance.

TYPICAL APPLICATIONS

- Pipework
- Petrochemical
- Nuclear Power generation

CLASSIFICATION

AWS A5.9 ER308L
EN ISO 14343-A W 19 9 L

SHIELDING GASES (ACC. EN ISO 14175)

I1 Inert gas Ar (100%)

APPROVALS

CE
+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.01	1.7	0.4	20	10	0.1

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
						+20 °C	-196 °C
Typical values	I1	AW	472	692	34	120	91

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
1,2	PE Tube	5.0	595460
1,6	PE Tube	5.0	595468
2,0	PE Tube	5.0	595470
2,4	PE Tube	5.0	595475
3,2	PE Tube	5.0	595482

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.