

LNT 310

TOP FEATURES

- High temperature ductility and excellent resistance to oxidation at working temperatures <1000°C.
- The weld deposit is fully austenitic
- Excellent corrosion resistance even when hot.

TYPICAL APPLICATIONS

- Heat Exchangers
- Hot water boilers
- Fabrication of furnaces

CLASSIFICATION

AWS A5.9 ER310
EN ISO 14343-A W 25 20

SHIELDING GASES (ACC. EN ISO 14175)

I1 Inert gas Ar (100%)

APPROVALS

CE

+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.1	1.7	0.5	26	21	0.1

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) +20°C
Typical values	I1	AW	360	600	35	100

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
1,6	PE Tube	5.0	604773
2,0	PE Tube	5.0	604790
2,4	PE Tube	5.0	604797
3,2	PE Tube	5.0	603295

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.

LNT 310-EN-05/09/22