

SUPRANOX RS 317L

TOP FEATURES

- Excellent weldability with a spatter free arc
- Self-releasing slag
- Very smooth bead appearance.

CLASSIFICATION

AWS A5.4 E317L-16
EN ISO 3581-A E Z (19 13 4 N L) R 12

CURRENT TYPE

DC+

WELDING POSITIONS

All position, except vertical down

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S	Cr	Ni	Mo	Ferrite
0.025	0.9	0.8	≤0.03	≤0.03	20	13	3.4	5-10

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Condition*		0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)		Impact ISO-V (J) 20°C
				4d	5d	
AWS A5.4	AW	not specified	≥520	≥30	not specified	not specified
EN ISO 3581-A	AW	≥350	≥550	not specified	≥25	not specified
Typical values	AW	450	600	33	≥30	45

* AW = As welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 300	50-80
3.2 x 350	60-120
4.0 x 350	100-140

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 300	VPMD	TBD	0.0	W100287838
	VPMD	90	1.7	W000287838
3.2 x 350	VPMD	TBD	0.0	W100287839
4.0 x 350	VPMD	TBD	0.0	W100287840

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.