

CARBOROD W 225V

TOP FEATURES

- It has a very low impurity deposit
- Used in the petrochemical industry for hydrocrackers and heavy wall pressure vessels for hydrogen service.

TYPICAL APPLICATIONS

- Petrochemical
- Pressure vessels
- Oil & Gas
- Heat Exchangers

CLASSIFICATION

AWS A5.28 ER 90S-G

SHIELDING GASES (ACC. EN ISO 14175)

I1 Inert gas Ar (100%)

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	Cr	Mo	Nb	V
≤0.13	≤1	≤0.2	2.5	1	0.02	0.25

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -29°C
Typical values	I1	PWHT 710°C x 8h	≥500	≥680	≥18	≥100

*PWHT = Post Welding Heat Treatment

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
2.4	PE Tube	5.0	W000289159

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.