

# ALMN

## TOP FEATURES

- Good weldability
- No porosity

## CLASSIFICATION

AWS A5.3	E3003
EN ISO 18273	Al 3103

## CURRENT TYPE

DC +

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

Al	Mn	Si	Zn	Fe	Cu	Mg	Others
bal.	0.9-1.2	0.3 max.	0.09 max.	0.6 max.	0.02 max.	0.15 max.	0.15 max.

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)
Typical values	AW	40	110	20

AW = As welded

## OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 350	40-70
3.2 x 350	60-90

## PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Pieces / unit	Weight (kg)	Item number
2.5x350	CAN	-	2.0	809718
3.2x350	CAN	-	2.0	800579

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.  
Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.