

KARDO

TOP FEATURES

- Low yield and ultimate tensile strength, high impact toughness
- Buffer layer electrode for internally clad stainless steel
- HDM < 3 ml/100g

CLASSIFICATION

AWS A5.1 E 6018 *
EN ISO 2560-A E 35 2 B 32 H5

* According to classification 1966

CURRENT TYPE

AC / DC (+/-)

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S	HDM
0.03	0.4	0.25	0.015	0.010	3 ml/100 g

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -18°C/-20°C
Required: AWS A5.1		min. 331	min. 414	min. 22	min. 27
EN ISO		min. 355	440-570	min. 22	
Typical values	AW	390	450	28	>200

AW = As welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5x350	60-80
3.2x350	90-120
4.0x350	120-160

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Pieces / unit	Weight (kg)	Item number
2.5x350	SRP	TBD	0.0	541762-1
3.2x350	SRP	TBD	0.0	541779-1
4.0x350	SRP	TBD	0.0	541755-1

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.

KARDO-EN-01/07/22