

MOLYCORD KV2L

TOP FEATURES

- The low carbon reduces the risk of cracking and promotes a lower tensile strength and hardness in the all weld metal deposit.
- Low diffusible hydrogen (HD<5ml/100g).
- Suitable for use with DC positive.

CLASSIFICATION

AWS A5.5	E7015-A1 H4
EN ISO 3580-A	E Mo B 22 H5

CURRENT TYPE

DC+

WELDING POSITIONS

All position, except vertical down

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S	Mo
0.05	0.70	0.35	≤0.015	≤0.015	0.5

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
					+20°C	-20°C
AWS A5.5	PWHT	≥390	≥520	≥19	not specified	not specified
EN ISO 3580-A	PWHT	≥355	≥510	≥20	≥47	not specified
Typical values	620°C x 1h	420	610	24	60	47

* PWHT: Postweld Heat Treatment 570-620°C / min 1h

Preheat and interpass temperature: <200°C

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 300	65-95
3.2 x 350	90-130
4.0 x 350	125-165

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 300	CBOH	TBD	0.0	W1013007012
3.2 x 350	CBOX	TBD	0.0	W1013007015
4.0 x 350	CBOX	TBD	0.0	W1013007016

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.